



Being the best through innovation

**SOLID CARBIDE**


# **TitaNox-POWER END MILLS**

- High Speed Machining for Exotic Materials:  
Titanium, Inconel and Stainless Steels

**UGMG42, UGMG43 SERIES 4 FLUTES DOUBLE CORE - Side Cutting**

SFM(Vc) = ft./min.  
IPT(fz) = in./tooth  
RPM = rev./min.  
IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)						
						1/4	5/16	3/8	1/2	5/8	3/4	1
P	1-5	Non-alloy steel	0.4D	1.0D (0.7D)*	SFM(Vc)	525	525	525	525	525	525	525
					IPT(fz)	.0011	.0014	.0017	.0021	.0025	.0030	.0033
	RPM	8020	6420	5350	4010	3210	2670	2010				
	IPM(FEED)	35	36	36	34	32	32	27				
	6-8	Low alloy steel	0.4D	1.0D (0.7D)*	SFM(Vc)	525	525	525	525	525	525	525
					IPT(fz)	.0011	.0014	.0017	.0021	.0025	.0030	.0033
	RPM	8020	6420	5350	4010	3210	2670	2010				
	IPM(FEED)	35	36	36	34	32	32	27				
	9	High alloyed steel, and tool steel	0.4D	1.0D (0.7D)*	SFM(Vc)	490	490	490	490	490	490	490
					IPT(fz)	.0010	.0014	.0017	.0019	.0025	.0028	.0033
RPM	7490	5990	4990	3740	2990	2500	1870					
IPM(FEED)	30	34	34	28	30	28	25					
10	High alloyed steel, and tool steel	0.4D	1.0D (0.7D)*	SFM(Vc)	490	490	490	490	490	490	490	
				IPT(fz)	.0011	.0014	.0018	.0021	.0026	.0030	.0033	
RPM	7490	5990	4990	3740	2990	2500	1870					
IPM(FEED)	33	34	36	31	31	30	25					
11.1	High alloyed steel, and tool steel	0.4D	1.0D (0.7D)*	SFM(Vc)	490	490	490	490	490	490	490	
				IPT(fz)	.0010	.0014	.0017	.0019	.0025	.0028	.0033	
RPM	7490	5990	4990	3740	2990	2500	1870					
IPM(FEED)	30	34	34	28	30	28	25					
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.4D	1.0D (0.7D)	SFM(Vc)	510	510	510	510	510	510	510
					IPT(fz)	.0013	.0018	.0022	.0026	.0034	.0037	.0045
	RPM	7790	6230	5190	3900	3120	2600	1950				
	IPM(FEED)	41	45	46	41	42	38	35				
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	0.4D	1.0D (0.7D)*	SFM(Vc)	345	345	345	345	345	345	345
					IPT(fz)	.0010	.0013	.0016	.0019	.0024	.0028	.0032
RPM	5270	4220	3510	2640	2110	1760	1320					
IPM(FEED)	21	22	22	20	20	20	17					
14.2	Stainless steel (SUS 630, PH 15-5)	0.4D	0.6D	SFM(Vc)	145	145	145	145	145	145	145	
				IPT(fz)	.0006	.0008	.0010	.0013	.0016	.0018	.0021	
RPM	2220	1770	1480	1110	890	740	550					
IPM(FEED)	5	6	6	6	6	5	5					
K	15-20	Grey cast iron	0.4D	1.0D (0.7D)*	SFM(Vc)	575	575	575	575	575	575	575
					IPT(fz)	.0008	.0011	.0014	.0017	.0021	.0024	.0028
					RPM	8790	7030	5860	4390	3510	2930	2200
					IPM(FEED)	28	31	33	30	29	28	25
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.3D	0.6D	SFM(Vc)	105	105	105	105	105	105	105
					IPT(fz)	.0008	.0010	.0013	.0015	.0019	.0022	.0026
					RPM	1600	1280	1070	800	640	530	400
					IPM(FEED)	5	5	6	5	5	5	4
36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.4D	1.0D (0.7D)*	SFM(Vc)	230	230	230	230	230	230	230	
				IPT(fz)	.0013	.0019	.0022	.0026	.0034	.0037	.0045	
				RPM	3510	2810	2340	1760	1410	1170	880	
				IPM(FEED)	18	21	21	18	19	17	16	



- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions


\* (0.7D): UGMG42K998, UGMG42K999, UGMGK801  
0.7D cutting depth for slotting and side cutting applications due to short double-core length

**UGMG42, UGMG43** SERIES

**4 FLUTES DOUBLE CORE - Slotting**

SFM(Vc) = ft./min.  
 IPT(fz) = in./tooth  
 RPM = rev./min.  
 IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)						
						1/4	5/16	3/8	1/2	5/8	3/4	1
P	1-5	Non-alloy steel	1.0D	1.0D (0.7D)*	SFM (Vc)	410	410	410	410	410	410	410
					IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0033
					RPM	6260	5010	4180	3130	2510	2090	1570
	6-8	Low alloy steel	1.0D	1.0D (0.7D)*	SFM (Vc)	410	410	410	410	410	410	410
					IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0033
					RPM	6260	5010	4180	3130	2510	2090	1570
	9	High alloyed steel, and tool steel	1.0D	1.0D (0.7D)*	SFM (Vc)	395	395	395	395	395	395	395
					IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0030
					RPM	6040	4830	4020	3020	2410	2010	1510
	10	High alloyed steel, and tool steel	1.0D	1.0D (0.7D)*	SFM (Vc)	410	410	410	410	410	410	410
IPT (fz)					.0010	.0013	.0017	.0019	.0025	.0028	.0033	
RPM					6260	5010	4180	3130	2510	2090	1570	
11.1	High alloyed steel, and tool steel	1.0D	1.0D (0.7D)*	SFM (Vc)	395	395	395	395	395	395	395	
				IPT (fz)	.0010	.0013	.0017	.0019	.0025	.0028	.0030	
				RPM	6040	4830	4020	3020	2410	2010	1510	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	1.0D	1.0D (0.7D)	SFM (Vc)	410	410	410	410	410	410	410
					IPT (fz)	.0013	.0018	.0022	.0026	.0032	.0037	.0041
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	1.0D	1.0D (0.7D)*	SFM (Vc)	280	280	280	280	280	280	280
					IPT (fz)	.0010	.0013	.0016	.0019	.0024	.0028	.0032
					RPM	4280	3420	2850	2140	1710	1430	1070
	14.2	Stainless steel (SUS 630, PH 15-5)	1.0D	0.5D	SFM (Vc)	120	120	120	120	120	120	120
					IPT (fz)	.0006	.0008	.0010	.0013	.0016	.0018	.0021
					RPM	1830	1470	1220	920	730	610	460
	K	15-20	Grey cast iron	1.0D	1.0D (0.7D)*	SFM (Vc)	460	460	460	460	460	460
IPT (fz)						.0008	.0011	.0014	.0017	.0021	.0024	.0026
RPM						7030	5620	4690	3510	2810	2340	1760
31-35		Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	1.0D	0.4D	SFM (Vc)	80	80	80	80	80	80	80
					IPT (fz)	.0007	.0009	.0012	.0014	.0017	.0020	.0022
					RPM	1220	980	810	610	490	410	310
36-37		Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	1.0D	1.0D (0.7D)*	SFM (Vc)	180	180	180	180	180	180	180
					IPT (fz)	.0013	.0018	.0022	.0026	.0034	.0037	.0041
					RPM	2750	2200	1830	1380	1100	920	690



**NOTES:** ▶ Maximum recommended depth shown

- ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
- ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
- ▶ Reduce speed and feed recommendations for materials harder than listed
- ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

\* (0.7D): UGMG42K998, UGMG42K999, UGMGK801  
 0.7D cutting depth for slotting and side cutting applications due to short double-core length




**UGMH12, UGMG32, UGMG34, UGMH06, UGMH07 SERIES**

SFM(Vc) = ft./min.  
IPT(fz) = in./tooth  
RPM = rev./min.  
IPM(Feed) = in./min.

**5 FLUTES - Side Cutting**

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)											
						1/8	3/16	1/4	5/16	3/8	1/2	9/16	5/8	11/16	3/4	1	1 1/4
P	1-5	Non-alloy steel	0.3D	1.5D	SFM(Vc)	470	470	470	470	470	470	470	470	470	470	470	470
					IPT(fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046
					RPM	14360	9570	7180	5740	4790	3590	3190	2870	2610	2390	1800	1440
	6-8	Low alloy steel	0.3D	1.5D	SFM(Vc)	470	470	470	470	470	470	470	470	470	470	470	470
					IPT(fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046
					RPM	14360	9570	7180	5740	4790	3590	3190	2870	2610	2390	1800	1440
9	High alloyed steel, and tool steel	0.3D	1.5D	SFM(Vc)	330	330	330	330	330	330	330	330	330	330	330	330	
				IPT(fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046	
				RPM	10080	6720	5040	4030	3360	2520	2240	2020	1830	1680	1260	1010	
10	High alloyed steel, and tool steel	0.3D	1.5D	SFM(Vc)	470	470	470	470	470	470	470	470	470	470	470	470	
				IPT(fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046	
				RPM	14360	9570	7180	5740	4790	3590	3190	2870	2610	2390	1800	1440	
11.1	High alloyed steel, and tool steel	0.3D	1.5D	SFM(Vc)	330	330	330	330	330	330	330	330	330	330	330	330	
				IPT(fz)	.0004	.0007	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	.0046	
				RPM	10080	6720	5040	4030	3360	2520	2240	2020	1830	1680	1260	1010	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.3D	1.5D	SFM(Vc)	385	385	385	385	385	385	385	385	385	385	385	
					IPT(fz)	.0003	.0004	.0009	.0010	.0012	.0018	.0020	.0021	.0022	.0024	.0028	.0033
					RPM	11760	7840	5880	4710	3920	2940	2610	2350	2140	1960	1470	1180
14.1	Stainless steel (SUS 316, 316, X5CrNiMo 17 12 2)	0.3D	1.5D	SFM(Vc)	270	270	270	270	270	270	270	270	270	270	270	270	
				IPT(fz)	.0004	.0005	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	.0041	
				RPM	8250	5500	4130	3300	2750	2060	1830	1650	1500	1380	1030	830	
14.2	Stainless steel (SUS 630, PH 15-5)	0.3D	1.5D	SFM(Vc)	195	195	195	195	195	195	195	195	195	195	195	195	
				IPT(fz)	.0004	.0005	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	.0041	
				RPM	5960	3970	2980	2380	1990	1490	1320	1190	1080	990	740	600	
K	15-20	Grey cast iron	0.3D	1.5D	SFM(Vc)	350	350	350	350	350	350	350	350	350	350	350	
					IPT(fz)	.0006	.0008	.0017	.0019	.0025	.0031	.0034	.0038	.0041	.0044	.0050	.0057
					RPM	10700	7130	5350	4280	3570	2670	2380	2140	1940	1780	1340	1070
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.1D	1.5D	SFM(Vc)	100	100	100	100	100	100	100	100	100	100	100	
					IPT(fz)	.0004	.0005	.0008	.0009	.0011	.0017	.0018	.0019	.0019	.0021	.0024	.0027
					RPM	3060	2040	1530	1220	1020	760	680	610	560	510	380	310
36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.2D	1.5D	SFM(Vc)	225	225	225	225	225	225	225	225	225	225	225		
				IPT(fz)	.0004	.0004	.0011	.0011	.0013	.0022	.0023	.0024	.0025	.0027	.0031	.0036	
				RPM	6880	4580	3440	2750	2290	1720	1530	1380	1250	1150	860	690	



- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

# TitaNox-POWER END MILLS


## RECOMMENDED CUTTING CONDITIONS

### EMI42, EMI43 SERIES

### 5 FLUTES (TitaNox-Power HPC) Heavy Side Cutting

SFM(Vc) = ft./min.  
IPT(fz) = in./tooth  
RPM = rev./min.  
IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)								
						3/16	1/4	5/16	3/8	1/2	5/8	3/4	1	
P	1-5	Non-alloy steel	0.5D	1.5D	SFM(Vc)	500	500	500	500	500	500	500	500	
					IPT(fz)	.0013	.0016	.0018	.0022	.0031	.0037	.0043	.0049	
					RPM	10190	7640	6110	5090	3820	3060	2550	1910	
	6-8	Low alloy steel	0.5D	1.5D	SFM(Vc)	500	500	500	500	500	500	500	500	
					IPT(fz)	.0013	.0016	.0018	.0022	.0031	.0037	.0043	.0049	
					RPM	10190	7640	6110	5090	3820	3060	2550	1910	
	9	Low alloy steel	0.5D	1.5D	SFM(Vc)	400	400	400	400	400	400	400	400	
					IPT(fz)	.0008	.0012	.0014	.0017	.0024	.0028	.0033	.0038	
					RPM	8150	6110	4890	4070	3060	2440	2040	1530	
	10	High alloyed steel, and tool steel	0.5D	1.5D	SFM(Vc)	450	450	450	450	450	450	450	450	
IPT(fz)					.0013	.0016	.0018	.0022	.0031	.0037	.0043	.0049		
RPM					9170	6880	5500	4580	3440	2750	2290	1720		
11.1	High alloyed steel, and tool steel	0.5D	1.5D	SFM(Vc)	400	400	400	400	400	400	400	400		
				IPT(fz)	.0008	.0012	.0014	.0017	.0024	.0028	.0033	.0038		
				RPM	8150	6110	4890	4070	3060	2440	2040	1530		
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.5D	1.5D	SFM(Vc)	250	250	250	250	250	250	250	250	
					IPT(fz)	.0007	.0010	.0012	.0015	.0021	.0024	.0028	.0032	
					RPM	5090	3820	3060	2550	1910	1530	1270	950	
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	0.5D	1.5D	SFM(Vc)	300	300	300	300	300	300	300	300	
					IPT(fz)	.0008	.0013	.0014	.0018	.0026	.0028	.0031	.0036	
					RPM	6110	4580	3670	3060	2290	1830	1530	1150	
	14.2	Stainless steel (SUS 630, PH 15-5)	0.5D	1.5D	SFM(Vc)	200	200	200	200	200	200	200	200	
					IPT(fz)	.0007	.0010	.0011	.0014	.0021	.0022	.0025	.0029	
					RPM	4070	3060	2440	2040	1530	1220	1020	760	
K	15-20	Grey cast iron	0.5D	1.5D	SFM(Vc)	370	370	370	370	370	370	370	370	
					IPT(fz)	.0010	.0014	.0016	.0019	.0026	.0032	.0037	.0042	
					RPM	7540	5650	4520	3770	2830	2260	1880	1410	
	S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.2D	1.5D	SFM(Vc)	90	90	90	90	90	90	90	90
						IPT(fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027
						RPM	1830	1380	1100	920	690	550	460	340
		36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.5D	1.5D	SFM(Vc)	160	160	160	160	160	160	160	160
						IPT(fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027
						RPM	3260	2440	1960	1630	1220	980	810	610



- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

HSS

CBN END MILLS

i-Xmill END MILLS

i-SMART MODULAR END MILLS

X5070 END MILLS

4G MILL END MILLS

X-POWER PRO END MILLS

**TitaNox-POWER END MILLS**

JET-POWER END MILLS

V7 PLUS A END MILLS

V7 MILL INOX

ALU-POWER HPC END MILLS

ALU-POWER END MILLS

D-POWER GRAPHITE END MILLS

STANDARD CARBIDE

ONLY ONE COATED PM60 END MILLS

SINE-POWER

TANK-POWER END MILLS

STANDARD COBALT & HSS

TECHNICAL DATA



# TitaNox-POWER END MILLS


## RECOMMENDED CUTTING CONDITIONS

### EMI42, EMI43 SERIES

### 5 FLUTES (TitaNox-Power HPC) Side Cutting (Peel Milling)

SFM(Vc) = ft./min.  
IPT(fz) = in./tooth  
RPM = rev./min.  
IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)							
						3/16	1/4	5/16	3/8	1/2	5/8	3/4	1
P	1-5	Non-alloy steel	0.08D	2.0D	SFM(Vc)	650	650	650	650	650	650	650	650
					IPT(fz)	.0018	.0022	.0026	.0031	.0043	.0051	.0060	.0068
	RPM	13240	9930	7950	6620	4970	3970	3310	2480				
	IPM(FEED)	119	109	103	103	107	101	99	84				
	6-8	Low alloy steel	0.08D	2.0D	SFM(Vc)	650	650	650	650	650	650	650	650
					IPT(fz)	.0018	.0022	.0026	.0031	.0043	.0051	.0060	.0068
	RPM	13240	9930	7950	6620	4970	3970	3310	2480				
	IPM(FEED)	119	109	103	103	107	101	99	84				
	9	Low alloy steel	0.08D	2.0D	SFM(Vc)	650	650	650	650	650	650	650	650
					IPT(fz)	.0011	.0017	.0020	.0024	.0033	.0040	.0046	.0053
RPM	13240	9930	7950	6620	4970	3970	3310	2480					
IPM(FEED)	73	84	80	79	82	79	76	66					
10	High alloyed steel, and tool steel	0.08D	2.0D	SFM(Vc)	580	580	580	580	580	580	580	580	
				IPT(fz)	.0018	.0022	.0026	.0031	.0043	.0051	.0060	.0068	
RPM	11820	8860	7090	5910	4430	3540	2950	2220					
IPM(FEED)	106	97	92	92	95	90	89	75					
11.1	High alloyed steel, and tool steel	0.08D	2.0D	SFM(Vc)	550	550	550	550	550	550	550	550	
				IPT(fz)	.0011	.0017	.0020	.0024	.0033	.0040	.0046	.0053	
RPM	11200	8400	6720	5600	4200	3360	2800	2100					
IPM(FEED)	62	71	67	67	69	67	64	56					
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.06D	2.0D	SFM(Vc)	350	350	350	350	350	350	350	350
					IPT(fz)	.0010	.0015	.0016	.0021	.0029	.0034	.0039	.0045
	RPM	7130	5350	4280	3570	2670	2140	1780	1340				
	IPM(FEED)	36	40	34	37	39	36	35	30				
	14.1	Stainless steel (SUS 316, 316, X5CrNiMo 17 122)	0.06D	2.0D	SFM(Vc)	425	425	425	425	425	425	425	425
					IPT(fz)	.0011	.0018	.0019	.0025	.0036	.0039	.0044	.0051
RPM	8660	6490	5190	4330	3250	2600	2160	1620					
IPM(FEED)	48	58	49	54	59	51	48	41					
14.2	Stainless steel (SUS 630, PH 15-5)	0.06D	2.0D	SFM(Vc)	300	300	300	300	300	300	300	300	
				IPT(fz)	.0010	.0014	.0015	.0020	.0029	.0031	.0035	.0041	
RPM	6110	4580	3670	3060	2290	1830	1530	1150					
IPM(FEED)	31	32	28	31	33	28	27	24					
K	15-20	Grey cast iron	0.07D	2.0D	SFM(Vc)	550	550	550	550	550	550	550	550
					IPT(fz)	.0014	.0020	.0022	.0027	.0037	.0045	.0052	.0059
					RPM	11200	8400	6720	5600	4200	3360	2800	2100
					IPM(FEED)	78	84	74	76	78	76	73	62
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4964, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.04D	2.0D	SFM(Vc)	120	120	120	120	120	120	120	120
					IPT(fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027
					RPM	2440	1830	1470	1220	920	730	610	460
					IPM(FEED)	7	9	9	9	9	8	7	6
36-37	Titanium Alloys (HB 400 Rm, HB 1050Rm TiAl6V4, 3.7165)	0.05D	2.0D	SFM(Vc)	300	300	300	300	300	300	300	300	
				IPT(fz)	.0006	.0010	.0012	.0014	.0019	.0021	.0023	.0027	
				RPM	6110	4580	3670	3060	2290	1830	1530	1150	
IPM(FEED)	18	23	22	21	22	19	18	16					



- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

# TitaNox-POWER END MILLS


## RECOMMENDED CUTTING CONDITIONS

### EMI42, EMI43 SERIES

### 5 FLUTES (TitaNox-Power HPC) Slotting

SFM(Vc) = ft./min.  
IPT(fz) = in./tooth  
RPM = rev./min.  
IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)							
						3/16	1/4	5/16	3/8	1/2	5/8	3/4	1
P	1-5	Non-alloy steel	1.0D	1.0D	SFM (Vc)	275	275	275	275	275	275	275	275
					IPT (fz)	.0010	.0013	.0015	.0018	.0024	.0029	.0034	.0039
					RPM	5600	4200	3360	2800	2100	1680	1400	1050
	6-8	Low alloy steel	1.0D	1.0D	SFM (Vc)	275	275	275	275	275	275	275	275
					IPT (fz)	.0010	.0013	.0015	.0018	.0024	.0029	.0034	.0039
					RPM	5600	4200	3360	2800	2100	1680	1400	1050
	9	Low alloy steel	1.0D	1.0D	SFM (Vc)	275	275	275	275	275	275	275	275
					IPT (fz)	.0006	.0010	.0011	.0014	.0019	.0023	.0026	.0030
					RPM	5600	4200	3360	2800	2100	1680	1400	1050
	10	High alloyed steel, and tool steel	1.0D	0.75D	SFM (Vc)	230	230	230	230	230	230	230	230
IPT (fz)					.0010	.0013	.0015	.0018	.0024	.0029	.0034	.0039	
RPM					4690	3510	2810	2340	1760	1410	1170	880	
11.1	High alloyed steel, and tool steel	1.0D	0.75D	SFM (Vc)	250	250	250	250	250	250	250	250	
				IPT (fz)	.0006	.0010	.0011	.0014	.0019	.0023	.0026	.0030	
				RPM	5090	3820	3060	2550	1910	1530	1270	950	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	1.0D	0.5D	SFM (Vc)	225	225	225	225	225	225	225	225
					IPT (fz)	.0006	.0008	.0009	.0012	.0017	.0019	.0022	.0026
					RPM	4580	3440	2750	2290	1720	1380	1150	860
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	1.0D	0.5D	SFM (Vc)	250	250	250	250	250	250	250	250
					IPT (fz)	.0006	.0010	.0011	.0014	.0021	.0023	.0025	.0029
					RPM	5090	3820	3060	2550	1910	1530	1270	950
	14.2	Stainless steel (SUS 630, PH 15-5)	1.0D	0.5D	SFM (Vc)	200	200	200	200	200	200	200	200
					IPT (fz)	.0006	.0008	.0009	.0011	.0017	.0018	.0020	.0023
					RPM	4070	3060	2440	2040	1530	1220	1020	760
K	15-20	Grey cast iron	1.0D	1.0D	SFM (Vc)	260	260	260	260	260	260	260	260
					IPT (fz)	.0008	.0011	.0013	.0015	.0021	.0026	.0030	.0034
					RPM	5300	3970	3180	2650	1990	1590	1320	990
S	31-35	Heat Resistant Super Alloys (X12NiCrAl 36-16, 1-4864, Inconel 718, NiCr20TiAl, 2-4631, NiCu30Al, 2-4375, G-X120Mn12, 1-3401)	1.0D	0.4D	SFM (Vc)	64	64	64	64	64	64	64	64
					IPT (fz)	.0005	.0008	.0010	.0011	.0015	.0017	.0019	.0021
					RPM	1300	980	780	650	490	390	330	240
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm, TiAl6V4, 3.7165)	1.0D	0.5D	SFM (Vc)	160	160	160	160	160	160	160	160
					IPT (fz)	.0005	.0008	.0010	.0011	.0015	.0017	.0019	.0021
					RPM	3260	2440	1960	1630	1220	980	810	610




- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

**GMG40** SERIES

**4 FLUTES DOUBLE CORE - Side Cutting**

SFM(Vc) = ft./min.  
 IPT(fz) = in./tooth  
 RPM = rev./min.  
 IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)							
						6.0	8.0	10.0	12.0	14.0	16.0	20.0	25.0
P	1-4	Non-alloy steel	0.4D	1.0D	SFM(Vc)	525	525	525	525	525	525	525	525
					IPT(fz)	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033
					RPM	8490	6370	5090	4240	3640	3180	2550	2040
					IPM(FEED)	37	36	35	36	33	32	31	27
					SFM(Vc)	490	490	490	490	490	490	490	490
					IPT(fz)	.0010	.0014	.0017	.0019	.0022	.0025	.0028	.0033
	5	Non-alloy steel	0.4D	1.0D	SFM(Vc)	490	490	490	490	490	490	490	490
					IPT(fz)	.0010	.0014	.0017	.0019	.0022	.0025	.0028	.0033
					RPM	7920	5940	4750	3960	3400	2970	2380	1900
					IPM(FEED)	32	33	32	30	30	30	27	25
					SFM(Vc)	525	525	525	525	525	525	525	525
					IPT(fz)	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033
6-7	Low alloy steel	0.4D	1.0D	SFM(Vc)	525	525	525	525	525	525	525	525	
				IPT(fz)	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033	
				RPM	8490	6370	5090	4240	3640	3180	2550	2040	
				IPM(FEED)	37	36	35	36	33	32	31	27	
				SFM(Vc)	490	490	490	490	490	490	490	490	
				IPT(fz)	.0010	.0014	.0017	.0019	.0022	.0025	.0028	.0033	
8-9	Low alloy steel	0.4D	1.0D	SFM(Vc)	490	490	490	490	490	490	490	490	
				IPT(fz)	.0010	.0014	.0017	.0019	.0022	.0025	.0028	.0033	
				RPM	7920	5940	4750	3960	3400	2970	2380	1900	
				IPM(FEED)	32	33	32	30	30	30	27	25	
				SFM(Vc)	490	490	490	490	490	490	490	490	
				IPT(fz)	.0011	.0014	.0018	.0021	.0024	.0026	.0030	.0033	
10-11.1	High alloyed steel, and tool steel	0.4D	1.0D	SFM(Vc)	490	490	490	490	490	490	490	490	
				IPT(fz)	.0011	.0014	.0018	.0021	.0024	.0026	.0030	.0033	
				RPM	7920	5940	4750	3960	3400	2970	2380	1900	
				IPM(FEED)	35	33	34	33	33	31	29	25	
				SFM(Vc)	510	510	510	510	510	510	510	510	
				IPT(fz)	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0045	
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.4D	1.0D	SFM(Vc)	510	510	510	510	510	510	510	
					IPT(fz)	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0045
					RPM	8250	6190	4950	4120	3530	3090	2470	1980
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	0.4D	1.0D	SFM(Vc)	345	345	345	345	345	345	345	
					IPT(fz)	.0010	.0013	.0016	.0019	.0022	.0024	.0028	.0032
					RPM	5580	4180	3350	2790	2390	2090	1670	1340
14.2	Stainless steel (SUS 630, PH 15-5)	0.4D	0.6D	SFM(Vc)	145	145	145	145	145	145	145		
				IPT(fz)	.0006	.0008	.0010	.0013	.0014	.0016	.0018	.0021	
				RPM	2340	1760	1410	1170	1000	880	700	560	
K	15-20	Grey cast iron	0.4D	1.0D	SFM(Vc)	575	575	575	575	575	575	575	
					IPT(fz)	.0008	.0011	.0014	.0017	.0019	.0021	.0024	.0028
					RPM	9300	6970	5580	4650	3980	3490	2790	2230
					IPM(FEED)	30	31	31	32	30	29	27	25
					SFM(Vc)	105	105	105	105	105	105	105	105
					IPT(fz)	.0008	.0010	.0013	.0015	.0017	.0019	.0022	.0026
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.3D	0.6D	SFM(Vc)	1700	1270	1020	850	730	640	510	410
					RPM	5	5	5	5	5	5	4	4
					IPM(FEED)	230	230	230	230	230	230	230	230
	36-37	Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	0.3D	0.6D	SFM(Vc)	230	230	230	230	230	230	230	230
					IPT(fz)	.0013	.0019	.0022	.0026	.0030	.0034	.0037	.0045
					RPM	3720	2790	2230	1860	1590	1390	1120	890
IPM(FEED)	19	21	20	19	19	19	17	16					



- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

# TitaNox-POWER END MILLS


## RECOMMENDED CUTTING CONDITIONS

### GMG40 SERIES

### 4 FLUTES DOUBLE CORE - Slotting

SFM(Vc) = ft./min.  
IPT(fz) = in./tooth  
RPM = rev./min.  
IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)										
						6.0	8.0	10.0	12.0	14.0	16.0	20.0	25.0			
P	1-4	Non-alloy steel	1.0D	1.0D	SFM(Vc)	410	410	410	410	410	410	410	410			
					IPT(fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0033			
					RPM	6630	4970	3980	3310	2840	2490	1990	1590			
	5		1.0D	1.0D	SFM(Vc)	395	395	395	395	395	395	395	395			
					IPT(fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0030			
					RPM	6390	4790	3830	3190	2740	2400	1920	1530			
	6-7	Low alloy steel	1.0D	1.0D	SFM(Vc)	410	410	410	410	410	410	410	410			
					IPT(fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0033			
					RPM	6630	4970	3980	3310	2840	2490	1990	1590			
	8-9		1.0D	1.0D	SFM(Vc)	395	395	395	395	395	395	395	395			
					IPT(fz)	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0030			
					RPM	6390	4790	3830	3190	2740	2400	1920	1530			
	10-11.1	High alloyed steel, and tool steel	1.0D	1.0D	SFM(Vc)	395	395	395	395	395	395	395	395			
					IPT(fz)	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033			
					RPM	6390	4790	3830	3190	2740	2400	1920	1530			
M	12-13		Stainless steel (SUS 420, X40Cr13, 420)	1.0D	1.0D	SFM(Vc)	410	410	410	410	410	410	410	410		
						IPT(fz)	.0013	.0018	.0022	.0026	.0029	.0032	.0037	.0041		
						RPM	6630	4970	3980	3310	2840	2490	1990	1590		
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)		1.0D	1.0D	SFM(Vc)	280	280	280	280	280	280	280	280		
						IPT(fz)	.0010	.0013	.0016	.0019	.0022	.0024	.0028	.0032		
						RPM	4530	3400	2720	2260	1940	1700	1360	1090		
	14.2		Stainless steel (SUS 630, PH 15-5)	1.0D	0.5D	SFM(Vc)	120	120	120	120	120	120	120	120		
						IPT(fz)	.0006	.0008	.0010	.0013	.0014	.0016	.0018	.0021		
						RPM	1940	1460	1160	970	830	730	580	470		
	K	15-20		Grey cast iron	1.0D	1.0D	SFM(Vc)	460	460	460	460	460	460	460	460	
							IPT(fz)	.0008	.0011	.0014	.0017	.0019	.0021	.0024	.0026	
							RPM	7440	5580	4460	3720	3190	2790	2230	1790	
		S	31-35		Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	1.0D	0.4D	SFM(Vc)	80	80	80	80	80	80	80	80
								IPT(fz)	.0007	.0009	.0012	.0014	.0016	.0017	.0020	.0022
								RPM	1290	970	780	650	550	490	390	310
36-37			Titanium Alloys (HB 400 Rm, HB 1050 Rm TiAl6V4, 3.7165)	1.0D		1.0D	SFM(Vc)	180	180	180	180	180	180	180	180	
							IPT(fz)	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0041	
							RPM	2910	2180	1750	1460	1250	1090	870	700	



- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C. (length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions



# TitaNox-POWER END MILLS


## RECOMMENDED CUTTING CONDITIONS

### GMG24, GMG26, GMG28, GMG30 SERIES

### 5 FLUTES - Side Cutting

SFM(Vc) = ft./min.  
IPT(fz) = in./tooth  
RPM = rev./min.  
IPM(Feed) = in./min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)									
						6.0	8.0	10.0	12.0	14.0	16.0	18.0	20.0	25.0	
P	1-4	Non-alloy steel	0.3D	1.5D	SFM (Vc)	475	475	475	475	475	475	475	475	475	
					IPT (fz)	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	
					RPM	7680	5760	4610	3840	3290	2880	2560	2300	1840	
					IPM (FEED)	50	43	46	48	44	43	42	40	37	
					SFM (Vc)	330	330	330	330	330	330	330	330	330	
					IPT (fz)	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	
	5	Non-alloy steel	0.3D	1.5D	SFM (Vc)	5340	4000	3200	2670	2290	2000	1780	1600	1280	
					IPT (fz)	35	30	32	33	31	30	29	28	26	
					RPM	330	330	330	330	330	330	330	330	330	
					IPM (FEED)	475	475	475	475	475	475	475	475	475	
					IPT (fz)	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040	
					RPM	7680	5760	4610	3840	3290	2880	2560	2300	1840	
6-7	Low alloy steel	0.3D	1.5D	SFM (Vc)	50	43	46	48	44	43	42	40	37		
				IPT (fz)	330	330	330	330	330	330	330	330	330		
				RPM	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040		
				IPM (FEED)	5340	4000	3200	2670	2290	2000	1780	1600	1280		
				SFM (Vc)	35	30	32	33	31	30	29	28	26		
				IPT (fz)	475	475	475	475	475	475	475	475	475		
8-9	Low alloy steel	0.3D	1.5D	SFM (Vc)	200	200	200	200	200	200	200	200	200		
				IPT (fz)	.0009	.0011	.0014	.0017	.0019	.0021	.0023	.0024	.0028		
				RPM	3230	2430	1940	1620	1390	1210	1080	970	780		
				IPM (FEED)	15	13	14	14	13	13	12	12	11		
				SFM (Vc)	385	385	385	385	385	385	385	385	385		
				IPT (fz)	.0009	.0010	.0012	.0018	.0020	.0021	.0022	.0024	.0028		
10-11.1	High alloyed steel, and tool steel	0.3D	1.5D	RPM	6230	4670	3740	3110	2670	2330	2080	1870	1490		
				IPM (FEED)	28	23	22	28	27	24	23	22	21		
				SFM (Vc)	270	270	270	270	270	270	270	270	270		
				IPT (fz)	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035		
				RPM	4370	3270	2620	2180	1870	1640	1460	1310	1050		
				IPM (FEED)	26	21	20	27	24	22	20	20	18		
M	12-13	Stainless steel (SUS 420, X40Cr13, 420)	0.3D	1.5D	SFM (Vc)	195	195	195	195	195	195	195	195		
					IPT (fz)	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	
					RPM	3150	2360	1890	1580	1350	1180	1050	950	760	
	14.1	Stainless steel (SUS 316, 316L, X5CrNiMo 17 12 2)	0.3D	1.5D	SFM (Vc)	19	15	14	20	18	16	15	14	13	
					IPT (fz)	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	
					RPM	4370	3270	2620	2180	1870	1640	1460	1310	1050	
14.2	Stainless steel (SUS 630, PH 15-5)	0.3D	1.5D	SFM (Vc)	350	350	350	350	350	350	350	350	350		
				IPT (fz)	.0017	.0019	.0025	.0031	.0034	.0038	.0041	.0044	.0050		
				RPM	5660	4240	3400	2830	2430	2120	1890	1700	1360		
K	15-20	Grey cast iron	0.3D	1.5D	IPM (FEED)	48	40	43	44	41	40	39	37	34	
					SFM (Vc)	100	100	100	100	100	100	100	100	100	
					IPT (fz)	.0008	.0009	.0011	.0017	.0018	.0019	.0019	.0021	.0024	
					RPM	1620	1210	970	810	690	610	540	490	390	
					IPM (FEED)	6	5	5	7	6	6	5	5	5	
					SFM (Vc)	225	225	225	225	225	225	225	225	225	
S	31-35	Heat Resistant Super Alloys (X12 NiCrSi 36-16, 1.4864, Inconel 718, NiCr20TiAl, 2.4631, NiCu30Al, 2.4375, G-X120Mn12, 1.3401)	0.1D	1.5D	IPT (fz)	.0011	.0011	.0013	.0022	.0023	.0024	.0025	.0027	.0031	
					RPM	3640	2730	2180	1820	1560	1360	1210	1090	870	
					IPM (FEED)	20	15	14	20	18	16	15	15	13	
	36-37	Titanium Alloys (HB 400 Rm, HB 1050Rm TiAl6V4, 3.7165)	0.3D	1.5D	SFM (Vc)	225	225	225	225	225	225	225	225	225	
					IPT (fz)	.0011	.0011	.0013	.0022	.0023	.0024	.0025	.0027	.0031	
					RPM	3640	2730	2180	1820	1560	1360	1210	1090	870	
IPM (FEED)	20	15	14	20	18	16	15	15	13						



- NOTES:**
- ▶ Maximum recommended depth shown
  - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
  - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
  - ▶ Reduce speed and feed recommendations for materials harder than listed
  - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions